

Annex 1

Digital light Processing (DLP) printer, operation software and parameter

Model (Picture)	Printer Manufacturer, Model	Light source	Light intensity	Operation Software	Parameter data set*
	Asiga Max	385 nm	6.1 mW/cm ²	Composer 1.2.11	Detax_Freeprint denture 385_5
	Asiga Max 2	385 nm	7.0 mW/cm ²	Composer 2.0.8	Detax_Freeprint denture 385_5
	Asiga Pico 2	385 nm	20 mW/cm ²	Composer 1.2.11	Detax_Freeprint denture 385_5
	Asiga PRO 2	385 nm	5.7 mW/cm ²	Composer 1.2.11	Detax_Freeprint denture 385_5
	Asiga PRO 4K	385 nm	7.0 mW/cm ²	Composer 1.2.11	Detax_Freeprint denture 385_5
	Asiga Ultra	385 nm	6.6 mW/cm ²	Composer 2.0.8	Detax_Freeprint denture 385_5

Annex 1

Digital light Processing (DLP) printer, operation software and parameter

Model (Picture)	Printer Manufacturer, Model	Light source	Light intensity	Operation Software	Parameter data set*
	Heygears UltraCraft A2D	385 nm	2.1 mW/cm ²	Materialise Magic 23	Detax Denture UV
	Microlay Versus	385 nm	4.3 mW/cm ²	Microform 1.0.3.7	DETX Freeprint denture 385 100 microns v5.3
	Miicraft Alpha	385 nm	6.0 mW/cm ²	Utility 6.3.4	DEATX freeprint denture
	Miicraft Ultra Series	385 nm	5.7 mW/cm ²	Utility 6.3.0	Detax_Freeprint denture UV_100
	Rapidshape D10+/D20+/D30+/D40+	385 nm	2.0 mW/cm ²	Netfabb 2020	DETX Freeprint-denture 385
	Way2Production SolFlex Series	385 nm	8.0 mW/cm ²	Netfabb 2020	Freeprint denture 385

*The set of parameters includes all relevant material and printer specific information

Cleaning Equipment

Cleaning unit

Manufacturer, Model	Cleaning process
---------------------	------------------

Rapidshape RS wash	Use the following settings: DETAX Freeprint-denture 385 Prior to post-exposure, check the openings, cavities and gap areas for residues. Then blow off with compressed air.
---------------------------	---

Ultrasonic bath Bandelin Sonorex	Clean the parts with isopropyl alcohol (purity $\geq 98\%$) for 3 minutes. Then thoroughly clean the openings, cavities and gap areas with compressed air. The main cleaning is performed in a separate vessel with fresh isopropyl alcohol (purity $\geq 98\%$) for 3 minutes. Prior to post-exposure, check the openings, cavities and gap areas for residues. Then blow off with compressed air.
---	--



detax GmbH

Carl-Zeiss-Str. 4 • 76275 Ettlingen • Germany
+49 7243 510 0 • post@detax.com • detax.com

07/2025

Light curing Equipment

Light Curing unit Manufacturer, Model	Curing process
Dentalfarm Photopol	2×3 min, progressive + N2, turn around components after 3 min
Heygears UltraCraft PCU 3.0	5 min under water
NK Optik Otoflash G171	2×2000 flashes under inert gas, turn around components after 2000 flashes
NK Optik Otoflash 250/500	4000 flashes under inert gas @15 Hz
Rapidshape RS cure	Use the following settings: DETAX Freeprint-denture 385
Rapidshape RS cure XL	Use the following settings: DETAX Freeprint-denture 385



detax GmbH

Carl-Zeiss-Str. 4 • 76275 Ettlingen • Germany
+49 7243 510 0 • post@detax.com • detax.com

07/2025